

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

JC05 Rec'd PCT/PTO

09/913118  
08 AUG 2001

In re Patent Application of Wolfgang RASP and Detlef HÜTT	
New U.S. National Stage Application of PCT/EP00/00853	Docket No.: 146154.00018
Filed: August 8, 2001	
For: TRANSPARENT, BIAXIALLY ORIENTED POLYOLEFIN FILM	


SAH  
#SA  
3-15-02

**PRELIMINARY AMENDMENT**

Honorable Commissioner of Patents  
and Trademarks  
Washington, D.C. 20231

**CERTIFICATE OF MAILING**

I hereby certify that this correspondence is being deposited with the United States Postal Service as first class mail in an envelope addressed to: Commissioner of Patents and Trademarks, Washington, D.C. 20231 on August 8, 2001.

By 

Sir:

Prior to examination of the above-identified application, Applicants respectfully request that the following amendments be entered into the application:

Changes to the Claims:

Please replace claims 3-13 with the following clean claims as follow:

- A
3. Polyolefin film according to claim 1, characterized in that the dry-grinding process is carried out in such a way that a rough surface structure is produced.
  4. Polyolefin film according to claim 1, characterized in that the ground layered silicate is non-glossy.

5. Polyolefin film according to claim 1, characterized in that the layered silicate is a mica, preferably muscovite, biotite, phlogopite, vermiculite or synthetic mica.

6. Polyolefin film according to claim 1, characterized in that the mica has optionally been ignited.

7. Polyolefin film according to claim 1, characterized in that the mean particle size is from 1 to 10  $\mu\text{m}$ , preferably from 2 to 8  $\mu\text{m}$ .

8. Polyolefin film according to claim 1, characterized in that the layered silicate is in the base layer and/or in one interlayer and/or in one top layer.

9. Polyolefin film according to claim 1, characterized in that the layered silicate is present in the film in a concentration of from 0.1 to 1.0  $\text{g/m}^2$ , preferably from 0.1 to 0.7  $\text{g/m}^2$ , in particular from 0.10 to 0.30  $\text{g/m}^2$ .

10. Polyolefin film according to claim 1, characterized in that the film has a thickness of from 3 to 10  $\mu\text{m}$ , preferably from 5 to 50  $\mu\text{m}$ .

11. Use of a film according to claim 1 for marking by means of a laser, preferably by means of a  $\text{CO}_2$  laser or by means of an Nd:YAG laser or by means of an excimer laser.

12. Use of an oriented laser-marked film according to claim 1 as packaging film.

13. Process for marking a film according to claim 1 by means of a laser.

---